



TIBCHEMICALS

PROTEGOL® EP Coating 32-89 S-L two-component epoxy coating

Description

PROTEGOL® EP Coating 32-89 S-L is a two-component epoxy coating. The product meets the requirements of DIN EN 10289:2002. Application is made by spatula, knife.

Uses

Internal and external coating of

- Pipes, pipe bends
- Fittings
- Tanks, containers

Benefits

- Excellent corrosion protection
- Good adhesion to steel
- Abrasion-resistant and impact-resistant
- Good chemical resistance

Referenced standards

DIN EN 10289:2002 Steel tubes and fittings for onshore and offshore pipelines - External liquid applied epoxy and epoxy-modified coatings

Product data

The following data has been obtained at +23°C unless otherwise stated:

Type	epoxide
Component A (base)	epoxide
Component B (hardener)	amine

Physical state:

Component A	pasty
Component B	pasty

Viscosity

Comp. A at 25 °C	9000 mPa*s
Comp. B at 25 °C	5000 mPa*s

Density(g/cm³)

Comp. A	1,52
Comp. B	1,39
Comp. A + B	1,47

Mixing Ratio Comp A : Comp B

Gravimetric	69:31
Volumetric	2,0:1,0

Coating properties

Recommended dry film thickness (DFT) ≥1500 µm

Actual required DFT may vary in certain applications, please contact us for technical clarification.

Service temperature -20 °C to 80 °C

T min substrate 10 °C

min. +3°C above dew point

Processing temperature

Component A	15 °C to 25 °C
Component B	15 °C to 25 °C

Max. relative air humidity 80 %

Potlife at 25 °C 25 min

Hardness Shore D 85 ±5

Release 7/7/2020

TIB Chemicals AG | Muelheimer Straße 16 -22 | 68219 Mannheim | P.O. 81 02 20 | 68202 Mannheim | GERMANY
Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | www.tib-chemicals.com

This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.





TIBCHEMICALS

PROTEGOL® EP Coating 32-89 S-L two-component epoxy coating

Impact resistance (max. impact energy)	5 J/mm
Adhesion to steel, pull off test	15 MPa
Cathodic disbondment after 28 d at 23 °C	2,30 mm
Specific electrical insulation resistance after 100 d at 23 °C	7,0 x 10 ⁹ Ωm ²
Thermal aging, adhesion, pull off test after 100 d at 100 °C	13 MPa
Cleaning agent	Solvent G
Repair material	
PROTEGOL® EP Coating 32-89 S/L	

Colours

Comp. A: yellow
 Comp. B: blue
 Comp. A+B: green
 Other colours on request (subject to technical feasibility and minimum order quantities)

Coverage, theoretical

Approx. 1,47 kg/m² at 1.000 µm DFT and not considering excess consumption.

Packaging

Component A	Component B
tin 1,38 kg	tin 0,62 kg

Shipping and Storage Regulations, Application, Health and Safety

Storage:

In a cool and dry place shelf life is approx. 24 months in tightly closed original packs.

Maintenance of tools:

Immediately after use, all tools should be cleaned with Solvent G.

Refer to our general work instructions for

PROTEGOL® Coatings.

Refer to our safety data sheets prior to use.

Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance to the safety data sheets.

Follow and observe any applicable local or national laws and regulations.

Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (DIN EN 16985 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355); furthermore, local laws and/or regulations must be observed.

Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand.

Release 7/7/2020

TIB Chemicals AG | Muelheimer Straße 16 -22 | 68219 Mannheim | P.O. 81 02 20 | 68202 Mannheim | GERMANY
 Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | www.tib-chemicals.com

This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.

