



# TIBCHEMICALS

## PROTEGOL® UR Coating 32-45 R Cartridge two-component polyurethane coating supplied in cartridges

### Description

PROTEGOL® UR Coating 32-45 R Cartridge is a two-component polyurethane coating supplied in cartridges. The product meets the requirements of DIN EN 10290:2002.

Application is made by pneumatic dispenser.

### Uses

External coating of

- Field joints
- Pipes, pipe bends
- Tanks, containers

### Benefits

- Excellent corrosion protection
- Abrasion-resistant and impact-resistant
- Easy to use
- Good chemical resistance
- No flushing - no solvent

### Referenced standards

**DIN EN 10290:2002** Steel tubes and fittings for onshore and offshore pipelines - External liquid applied polyurethane and polyurethane-modified coatings

### Product data

The following data has been obtained at +23°C unless otherwise stated:

Type	polyurethane
Component A (base)	polyol
Component B (hardener)	isocyanate

Physical state:

Component A	pasty
Component B	liquid

Viscosity

Comp. A at 50 °C	2500 mPa*s
Comp. B at 25 °C	200 mPa*s

Density (g/cm<sup>3</sup>)

Comp. A	1,50
Comp. B	1,24
Comp. A + B	1,44

Mixing Ratio Comp A : Comp B

Gravimetric	78,5:21,5
Volumetric	3,0:1,0

### Coating properties

Recommended dry film thickness (DFT) ≥1500 µm

Actual required DFT may vary in certain applications, please contact us for technical clarification.

Overcoating period, min. 3 min

Service temperature -20 °C to 80 °C

Short term temperature load without temperature gradient to the substrate 110 °C

T min substrate 10 °C

min. +3°C above dew point

T min / max Component A 30 °C / 45 °C

T min / max Component B 30 °C / 45 °C

Max. relative air humidity 80 %

Potlife at 40 °C 120 sec.

Hardness Shore D 70 ±5

Release 7/7/2020

TIB Chemicals AG | Muelheimer Straße 16 -22 | 68219 Mannheim | P.O. 81 02 20 | 68202 Mannheim | GERMANY  
Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | [www.tib-chemicals.com](http://www.tib-chemicals.com)

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*





# TIBCHEMICALS

## PROTEGOL® UR Coating 32-45 R Cartridge two-component polyurethane coating supplied in cartridges

Impact resistance (max. impact energy)	8 J/mm
Adhesion to steel, pull off test	11 MPa
Cathodic disbondment after 28 d at 23 °C	4,60 mm
Specific electrical insulation resistance after 100 d at 23 °C	11x10 <sup>9</sup> Ωm <sup>2</sup>
Thermal aging, adhesion, pull off test after 100 d at 100 °C	16 MPa
Flexural strength	Req. fulfilled
Elongation at break [%]	18
Cleaning agent	Solvent B, G
Repair material	
PROTEGOL® PU Repair,	
PROTEGOL® UR Coating 32-45/55 L (Cartridge),	
PROTEGOL® UR Coating 32-60 (Cartridge)	

Refer to our general work instructions for PROTEGOL® Coatings.  
Refer to our safety data sheets prior to use. Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance to the safety data sheets. Follow and observe any applicable local or national laws and regulations.  
Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (DIN EN 16985 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355)); furthermore, local laws and/or regulations must be observed.  
Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand.

### Colours

RAL 9011 - Graphite black  
Other colours on request (subject to technical feasibility and minimum order quantities)

### Coverage, theoretical

Approx. 1,44 kg/m<sup>2</sup> at 1.000 µm DFT and not considering excess consumption.

### Packaging

Component A	Component B
2K cartridge 1,13 kg	0,31 kg

### Shipping and Storage Regulations, Application, Health and Safety

#### Storage:

In a cool and dry place shelf life is approx. 12 months in tightly closed original packs.

#### Maintenance of tools:

Immediately after use, all tools should be cleaned with Solvent B, G.

Release 7/7/2020

TIB Chemicals AG | Muelheimer Straße 16 -22 | 68219 Mannheim | P.O. 81 02 20 | 68202 Mannheim | GERMANY  
Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | [www.tib-chemicals.com](http://www.tib-chemicals.com)

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

