

PROTEGOL® UR Coating 32-45/55 L two-component polyurethane coating

Description

PROTEGOL® UR Coating 32-45/55 L is a two-component polyurethane coating. The product meets the requirements of DIN EN 10290:2002. Application is made by spatula, knife or brush. The product is a complementary product to PROTEGOL® UR Coatings for manual processing.

Uses

Coating of

- Field joints
- Pipes, pipe bends
- Fittings
- Tanks, containers
- Repair of coating imperfections
- Stripe coating of parts of complex shapeenvironment

Benefits

- Excellent corrosion protection
- Abrasion resistant
- Impact resistant
- Good chemical resistance

Referenced standards

DIN EN 10290:2002 Steel tubes and fittings for onshore and offshore pipelines - External liquid applied polyurethane and polyurethane-modified coatings

Product data

The following data has been obtained at +23°C unless otherwise

stated:

Type polyurethane
Component A (base) polyol
Component B (hardener) isocyanate

Physical state:

Component A pasty
Component B liquid

Viscosity

Comp. A at 25 °C 16300 mPa*s Comp. B at 25 °C 200 mPa*s

Density (g/cm³)

Comp. A 1,49 Comp. B 1,24 Comp. A + B 1,43

Mixing Ratio Comp A: Comp B

Gravimetric 78,5:21,5 Volumetric 3,0:1,0

Coating properties

Recommended dry film thickness (DFT) ≥1500 µm

Actual required DFT may vary in certain applications, please contact us for technical

Overcoating period, min. 1 h

Service temperature -20 °C to 80 °C

Short term temperature load without

temperature gradient to the substrate 110 °C T min substrate 10 °C

min. +3°C above dew point Processing temperature

Component A 15 °C to 25 °C Component B 15 °C to 25 °C

Max. relative air humidity 80 %

Potlife at 23 °C 20 min

Hardness Shore D 70 ±5

Release 7/7/2020

TIB Chemicals AG | Muelheimer Straße 16 -22 | 68219 Mannheim | P.O. 81 02 20 | 68202 Mannheim | GERMANY Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | www.tib-chemicals.com





PROTEGOL® UR Coating 32-45/55 L two-component polyurethane coating

Adhesion to steel, pull off test 16 MPa

Cathodic disbondment after 28 d

at 23 °C 3,30 mm

Specific electrical insulation resistance

after 100 d at 23 °C >10^7 Ωm²

Flexural strength Req. fulfilled

Elongation at break [%]

Cleaning agent Solvent B, G

Colours

RAL 9011 - Graphite black RAL 5005 - Signal blue

Other colours on request (subject to technical feasibility and minimum order quantities)

Coverage, theoretical

Approx. 1,43 kg/m² at 1.000 μ m DFT and not considering excess consumption.

Packaging

Component A Component B tin 1,57 kg tin 0,43 kg

Shipping and Storage Regulations, Application, Health and Safety

Storage:

In a cool and dry place shelf life is approx. 24 months in tightly closed original packs.

Maintenance of tools:

Immediately after use, all tools should be cleaned with Solvent B, G.

Refer to our general work instructions for PROTEGOL® Coatings
Refer to our safety data sheets prior to use.
Carefully read and follow all safety instructions on

labels and packaging. Handle and store material with care in accordance to the safety data sheets. Follow and observe any applicable local or national laws and regulations.

Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (DIN EN 16985 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355)); furthermore, local laws and/or regulations must be observed.

Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand

Release 7/7/2020

